



HIPS 7026

Product Description:

HIPS-7026 gives excellent processing in both extrusion with good finished product dimensional stability.

Application:

It use for wide range of extrusion, for sheet, disposable dishware, electronic packaging, cable reels. . Air ducting for car heater, TV and tape recorder equipment.

PROPERTY	VALUE	UNIT	TEST METHOD
Melt Flow Rate (200°C/5 Kg)	2.4	g/10min	ASTM D-1238
Tensile strength	30	MPa	ASTM D-638
Flexural modulus	2100	MPa	ASTM D-790
Charpy Izod impact strength	12.5	KJ/m ²	ASTM D-256
Vicat softening point at 120°C, 1 kg	96	°C	ASTM D-1525

All above mentioned data are typical values and not to be construed as real specifications. Users should confirm results by their own tests.